



# DYNAGRIP®

THE GRIP THAT OUTPERFORMS™

## 4000® SUBFLOOR

*Exceptional Bond Strength in the Most Extreme Conditions.*



**EASY TO GUN  
IN COLD TEMPS**

*Adhesive won't freeze, easier to gun in the cold*



**BONDS WET, FROZEN  
& TREATED LUMBER**

*Excellent adhesion in extreme weather conditions*



**HIGH STRENGTH  
WEATHERPROOF BOND**

*Prevents floor squeaks & improves structural performance of subfloor assembly*



**Exterior / Interior**  
CONSTRUCTION ADHESIVE



# DYNAGRIP®

THE GRIP THAT OUTPERFORMS™

## 4000® SUBFLOOR



**BONDS WET, FROZEN  
& TREATED LUMBER**



DYNAGRIP 4000 SUBFLOOR



LIQUID NAILS®



TITEBOND®

Shear Strength to Dry Lumber (psi)*	406	155	274
Shear Strength to Wet Lumber (psi)*	222	187	196
Shear Strength to Frozen Lumber (psi)*	248	149	221

\*Pounds per square inch of force required to break bond of adhesive on wet, frozen or treated lumber

### FEATURES



**Bonds to Wet & Frozen Lumber**



**Prevents Floor Squeaks**



**Permanent Bond**



**Will Not Freeze**

### PRODUCT DETAILS

#### RECOMMENDED USE

Subfloor, wood-to-wood assemblies, glued floor systems & deck installation.

#### NOT RECOMMENDED FOR

Most plastics, foamboard, mirror installation, constant water exposure, bonding two non-porous materials, or applications other than subfloor & deck installation.

#### ADHERES TO

- Plywood
- Enhanced OSB
- Concrete
- OSB
- Masonry
- Treated Lumber

#### TYPICAL PHYSICAL PROPERTIES

**Solids:** 61% - 65% by weight  
**Shelf Life:** 18 months  
**Skin Time:** 15 minutes  
**Cure Time:** 7-14 days

**Coverage:**  
**10.3 FL. OZ.**  
1/4" bead yields 32 linear ft.  
3/8" bead yields 14 linear ft.  
**28 FL. OZ.**  
1/4" bead yields 86 linear ft.  
3/8" bead yields 38 linear ft.

#### APPLICATION TEMPERATURE

0°F - 120°F

#### SERVICE TEMPERATURE

-20°F - 140°F

#### SPECIFICATIONS

ASTM D3498  
AFG-01  
PFS Certified

Meets or Exceeds  
Meets or Exceeds  
Tested in  
accordance with

### SKU SPECIFICATIONS

Product Name	Size	Package Code	GTIN	Case Pack	Case Weight	Case Dims. (LxWxH)	Case Volume (cu. ft.)	Cases Per Pallet
DynaGrip 4000 Subfloor	10.3 OZ.	0 70798 27517 1	100 70798 27517 8	12	10.59 lbs.	8" x 6" x 12"	0.33	108
DynaGrip 4000 Subfloor	28 OZ.	0 70798 25117 5	100 70798 25117 2	12	27.65 lbs.	10.5" x 8" x 17"	0.83	60

Liquid Nails® The Registered Trademark of PPG Architectural Finishes, Inc. Titebond® The Registered Trademark of Franklin International, Inc.

40006 (11/16)